

VALOX™ RESIN K4560

REGION ASIA

DESCRIPTION

30% glass reinforced PBT. Impact modified, high flow, hydrolytically stable.

TYPICAL PROPERTY VALUES

Revision 20180905

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yield	106	MPa	SABIC - Japan Method
Tensile Strain, break	4 – 4	%	SABIC - Japan Method
Flexural Stress	174	MPa	ASTM D 790
Flexural Modulus	6200	MPa	ASTM D 790
IMPACT			
Izod Impact, notched, 23°C	96	J/m	ASTM D 256
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	200	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	220	°C	ASTM D 648
PHYSICAL			
Specific Gravity	1.5	-	ASTM D 792
Mold Shrinkage, flow, 3.2 mm	0.6 – 0.8	%	SABIC method
Mold Shrinkage, flow, 6.4 mm	1 – 1.2	%	SABIC method

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.