

LNPTM THERMOTUFTM COMPOUND WF006NIQ

DESCRIPTION

LNP THERMOTUF WF006NIQ (Formerly known under the experimental grade name as EXTC8481) is an iQ PBT based compound containing 30% glass for NMT application. Added features of this material include: >25% PCR, high flow, high metal bonding strength, and good chemical resistance.

TYPICAL PROPERTY VALUES

Revision 20200521

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	110	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.5	%	ASTM D 638
Tensile Modulus, 5 mm/min	8760	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	170	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	7700	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	111	MPa	ISO 527
Tensile Strain, break, 5 mm/min	2.5	%	ISO 527
Tensile Modulus, 1 mm/min	8600	MPa	ISO 527
Flexural Stress, break, 2 mm/min	168	MPa	ISO 178
Flexural Modulus, 2 mm/min	7100	MPa	ISO 178
Bonding Strength ("T" treatment, shear type)	33	MPa	ISO 19095
IMPACT			
Izod Impact, unnotched, 23°C	870	J/m	ASTM D 4812
Izod Impact, notched, 23°C	137	J/m	ASTM D 256
Izod Impact, notched, -30°C	100	J/m	ASTM D 256
Izod Impact, unnotched 80*10*4 +23°C	54	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	13	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	10	kJ/m ²	ISO 180/1A
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	162	°C	ASTM D 648
HDT, 0.45 MPa, 3.2 mm, unannealed	204	°C	ASTM D 648
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	156	°C	ISO 75/Af
HDT/Bf, 0.45 MPa Flatw 80*10*4 sp=64mm	200	°C	ISO 75/Bf
CTE, 23°C to 50°C, flow	2.4E-05	1/°C	ASTM E 831
CTE, 23°C to 50°C, xflow	9.0E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, flow	2.4E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	8.1E-05	1/°C	ASTM E 831
CTE, 23°C to 50°C, flow	2.3E-05	1/°C	ISO 11359-2
CTE, 23°C to 50°C, xflow	9.6E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, flow	2.3E-05	1/°C	ISO 11359-2
CTE, -40°C to 40°C, xflow	8.6E-05	1/°C	ISO 11359-2
Relative Temp Index, Elec ⁽¹⁾	75	°C	UL 746B
Relative Temp Index, Mech w/impact ⁽¹⁾	75	°C	UL 746B
Relative Temp Index, Mech w/o impact ⁽¹⁾	75	°C	UL 746B
PHYSICAL			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Density	1.49	g/cm ³	ISO 1183
Melt Flow Rate, 250°C/5.0 kgf	21	g/10 min	ASTM D 1238
Melt Flow Rate, 275°C/5 kgf	37	g/10 min	ASTM D 1238
Melt Volume Rate, MVR at 250°C/5.0 kg	15	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 275°C/5 kg	29	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 270°C/5 kg	23	cm ³ /10 min	ISO 1133
Mold Shrinkage, flow	0.27	%	SABIC method
Mold Shrinkage, xflow	0.49	%	SABIC method
ELECTRICAL			
Dielectric Constant, 1.1 GHz	3.61	-	SABIC method
Dissipation Factor, 1.1 GHz	0.013	-	SABIC method
Dielectric Constant, 1.9 GHz	3.62	-	SABIC method
Dissipation Factor, 1.9 GHz	0.012	-	SABIC method
Dielectric Constant, 5 GHz	3.59	-	SABIC method
Dissipation Factor, 5 GHz	0.01	-	SABIC method
Dielectric Constant, 10 GHz	3.53	-	SABIC method
Dissipation Factor, 10 GHz	0.009	-	SABIC method
FLAME CHARACTERISTICS ⁽¹⁾			
UL Yellow Card Link	E207780-104030009	-	-
UL Recognized, 94HB Flame Class Rating	≥0.7	mm	UL 94
INJECTION MOLDING			
Drying Temperature	100 – 120	°C	
Drying Time	2 – 4	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 270	°C	
Nozzle Temperature	255 – 275	°C	
Front - Zone 3 Temperature	250 – 270	°C	
Middle - Zone 2 Temperature	250 – 270	°C	
Rear - Zone 1 Temperature	240 – 260	°C	
Hopper Temperature	40 – 60	°C	
Mold Temperature	100 – 160	°C	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.