

EXTEM™ RESIN XH1015UCL

DESCRIPTION

EXTEM XH1015UCL resin is an unreinforced amorphous thermoplastic polyimide (TPI) resin that may offer a high glass transition temperature (Tg) of 267°C. Features are excellent mechanical, electrical and dimensional properties up to high temperatures. The material has good near-IR transparency and a high refractive index making it an excellent candidate for SMT needing injection moldable optical lenses and connectors. The material is RoHS compliant and the natural, uncolored, material is halogen free according to standards IEC 61249-2-21, IPC 4101E and JEDEC JS709B. For colored variants compliance needs to be checked case by case.

GENERAL INFORMATION	
Features	Flame Retardant, Chemical Resistance, Good Processability, High Flow, Low Warpage, Low Smoke and Toxicity, Thin Wall, Dielectrics, Amorphous, Low Shrinkage, IR Transparent, Lead free reflow soldering capable, Low Moisture Absorption, Low Extractable, Transparent/Translucent, Non Cl/Br flame retardant, Non halogenated flame retardant, Low ionics/Outgassing/Liquid particle count, Creep resistant, Dimensional stability, High stiffness/Strength, High temperature resistance
Fillers	Unreinforced
Polymer Types	Thermoplastic Polyimide (TPI)
Processing Techniques	SMT, Micro molding, Lead free soldering, Injection Molding
Regional Availability	Europe, Asia, Americas

INDUSTRY	SUB INDUSTRY
Electrical and Electronics	Mobile Phone - Computer - Tablets
Industrial	Electrical, Material Handling

TYPICAL PROPERTY VALUES

Revision 20220721

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL ⁽¹⁾			
Tensile Stress, yld, Type I, 5 mm/min	103	MPa	ASTM D638
Tensile Stress, brk, Type I, 5 mm/min	96	MPa	ASTM D638
Tensile Strain, yld, Type I, 5 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	10	%	ASTM D638
Tensile Modulus, 5 mm/min	3420	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	168	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	3130	MPa	ASTM D790
Tensile Stress, yield, 5 mm/min	101	MPa	ISO 527
Tensile Stress, break, 5 mm/min	74	MPa	ISO 527
Tensile Strain, yield, 5 mm/min	6	%	ISO 527
Tensile Strain, break, 5 mm/min	7	%	ISO 527
Tensile Modulus, 1 mm/min	3100	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	120	MPa	ISO 178
Flexural Modulus, 2 mm/min	2870	MPa	ISO 178
IMPACT ⁽¹⁾			
Izod Impact, notched, 23°C	43	J/m	ASTM D256
Izod Impact, notched 80°10*4 +23°C	4	kJ/m ²	ISO 180/1A
THERMAL ⁽¹⁾			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Vicat Softening Temp, Rate B/50	260	°C	ASTM D1525
HDT, 0.45 MPa, 3.2 mm, unannealed	250	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	235	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	237	°C	ASTM D648
CTE, 23°C to 150°C, flow	5.E-05	1/°C	ISO 11359-2
CTE, 23°C to 150°C, xflow	5.1E-05	1/°C	ISO 11359-2
Vicat Softening Temp, Rate B/50	250	°C	ISO 306
Vicat Softening Temp, Rate B/120	247	°C	ISO 306
HDT/Af, 1.8 MPa Flatw 80*10*4 sp=64mm	223	°C	ISO 75/Af
PHYSICAL ⁽¹⁾			
Specific Gravity	1.31	-	ASTM D792
Water Absorption, (23°C/48hrs)	0.6	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm ⁽²⁾	1 – 1.2	%	SABIC method
Melt Flow Rate, 367°C/6.6 kgf	10	g/10 min	ASTM D1238
Density	1.31	g/cm ³	ISO 1183
Water Absorption, (23°C/saturated)	2.3	%	ISO 62-1
OPTICAL ⁽¹⁾			
Light Transmission			
at 1.0 mm and 850 nm	82	%	ASTM D1003
at 1.0 mm and 1350 nm	87	%	ASTM D1003
Refractive Index			
at 850 nm	1.633	-	ISO 489
at 1350 nm	1.622	-	ISO 489
Abbe number	18	-	ISO 489
ELECTRICAL ⁽¹⁾			
Dielectric Constant (Dk), 1 KHz	3.5	-	ASTM D150
Dielectric Constant, 1 MHz	3.4	-	ASTM D150
Comparative Tracking Index	125	V	IEC 60112
Dielectric Strength, in air, 1.6 mm	25	kV/mm	ASTM D149
INJECTION MOLDING ⁽³⁾			
Drying Temperature	175	°C	
Drying Time	4 – 6	Hrs	
Drying Time (Cumulative)	24	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	380 – 410	°C	
Nozzle Temperature	375 – 405	°C	
Front - Zone 3 Temperature	380 – 410	°C	
Middle - Zone 2 Temperature	370 – 400	°C	
Rear - Zone 1 Temperature	360 – 385	°C	
Mold Temperature	160 – 200	°C	
Intake (throat) temperature	70 – 100	°C	
Back pressure (Plastic Pressure)	40 – 70	MPa	
Screw speed (Circumferential speed)	<0.2	m/s	
Shot to Cylinder Size	40 – 70	%	
Vent Depth	0.025 – 0.076	mm	

- (1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.
- (2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.
- (3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.