



SABIC® PPcompound H1030

Mineral reinforced impact modified polypropylene

Development October 2017

Description

SABIC®PPcompound H1030 is a high flow, halogen free flame redardant, homopolymer with 30% glass fiber, developed for electrical & electronic injection molded applications. This material has been designed to combine a good performance profile with good processing.

SABIC®PPc H1030 is a designated injection molded grade for electrical applications.

IMDS: na				
Typical values		Revision: 3-10-2017		
Properties		Unit (Si)	Values	Test methods
Physical properties				
Melt flow rate (MFR)				ISO 1133
at 230 °C and 2.16 kg		g/10 min	8	
Density	1)	kg/m³	1200	ISO 1183
Filler content		%	30	
Mould shrinkage	2)			SABIC method
24 hours after injection moulding		%	-	
Mechanical properties				
Tensile test	1)			ISO 527/1A
Tensile modulus		MPa	8500	
stress at yield		MPa	-	
stress at break		MPa	100	
strain at break		%	3	
Flexural test	1)			ISO 178
Flexural modulus		MPa	7800	
Charpy impact notched	1)			ISO 179/1eU
at 23 °C		kJ/m²	9	
Charpy impact notched	1)			ISO 179/1eA
at 23 °C		kJ/m²	44	
Thermal properties				
Heat deflection temperature	1)			ISO 75 (flatwise)
HDT A (at 1.8 MPa)		°C	148	
HDT B (at 0.45 MPa)		°C	159	
СТІ		V	600	IEC 60112 sol. A
UL94 at 0.8mm		-	V2	
UL94 at 1.5mm		-	V0	
UL94 at 3.0mm		-	5V	
GWFI at 0.8mm		°C	960	
GWFI at 1.6mm		°C	960	

Injection molded sample ISO527-1A.
Injection molded plaque 65x65x3.2 mm

All information supplied by or on behalf of any of the SABIC Europe companies in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but the relevant SABIC Europe company assumes no liability whatsoever in respect of application, processing or use made of the afore-mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore-mentioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to any of the SABIC Europe companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the afore-mentioned information or products by the user.

Internet www.sabic-europe.com